

BELLUCCI

TECHNICAL SHEET

living glass future®

CATEGORY	TEMPERING FURNACE
BRAND	M A P P I
MODEL	A U 1 F 1 S 1 2 0 0 3 0 0 0 O . 4 . S .
YEAR	1 9 9 6
THICKNESS	4-19 MM
WORKING DIMENSIONS	1 2 0 0 X 3 0 0 0 M M
DETAILS	C A N D O 1 2 5 0 M M
	☐ ☐ ☐ ☐



***** SET MACCHINA *****									
TEMPERATURA CAMERA	668	668	TEMP. MASTER	19	Tempi carrelli precedenti				
TEMPERATURA USCITA	668	668	LETT. PIROMETRO	0					
DIFFER. TEMP. SUP/INF	0	0							
PERCENT. CONDUZIONE	0	0							
TEMPO BASE	320	320	Attuale	0	0	0	0	0	0
DURATA FASE TEMpra	120	120	Attuale	0	0	0	0	0	0
VELOCITA' TEMpra	70	70			0	0	0	0	0
VELOCITA' RAFFREDDAM.	90	90			0	0	0	0	0
VELOCITA' RIPOSO	50	50			0	0	0	0	0
POSIZ. SOFFIAN. SUPER.	Set	655	Attuale	653	0	0	0	0	0
POSIZ. SOFFIAN. INFER.	Set	555	Attuale	557	0	0	0	0	0
VELOCITA' OSCILLAZIONE	80	Set	80		0	0	0	0	0
VELOCITA' TRASLAZIONE	80	Set	80		0	0	0	0	0
SPESSORE 4 mm	0	0			0	0	0	0	0
PARZ. SOFFIANTE 1	0	0			0	0	0	0	0
PARZ. SOFFIANTE 2	0	0			0	0	0	0	0
1START	2TEM.ATT.	3IND.ALL.	4COMANDI	5CURVA T. 6	7	8			
9	10AGG.TEM. 11	12	13	14	15	16			